

# **Nomex<sup>®</sup> Polyester Nomex<sup>®</sup>**

Nomex<sup>®</sup> Polyester Nomex<sup>®</sup> is a triple layered laminate with polyester film sandwiched in between two layers of DuPont<sup>™</sup> Nomex<sup>®</sup> aramid - 2mil thickness paper bonded with a high temperature adhesive system. The product is designed not to delaminate or blister at elevated temperatures. This semi rigid laminate exhibits a high dielectric strength, as well as good initial tear and tensile strengths. The high abrasion properties allow the product to be inserted easily in the slot portions of a stator without damaging the insulation properties.

### Application

These laminates find a popular use in the manufacture and repair of motors and generators of various ratings and temperature class. Popularly used as slot liners in stators, as wedges and phase insulation in motors and generators, as well as large special F class motors.

### Availability

These laminates are available in standard widths of 900mm in continuous rolls in various thickness and constructions. Slitted Tapes to specific sizes are also available upon request to facilitate auto slot insertion process in small stators. Laminates with 1.5mil base DuPont<sup>™</sup>Nomex<sup>®</sup> paper (with a prominent orange lining) are also available on request.

## Shelf Life

Nomex<sup>®</sup> Polyester Nomex<sup>®</sup> exhibits a shelf life of 12 months from date of manufacture when stored at 25°C temperature and 50% relative humidity.

Item	Unit	Nomex Polyester Nomex – Yellow Line							
Thickness	mm	0.14	0.17	0.19	0.22	0.24	0.31	0.37	0.47
Substance	GSM	145	180	210	240	275	365	470	590
Film thickness	mic	23	50	75	100	125	190	250	350
Construction		2-1-2	2-2-2	2-3-2	2-4-2	2-5-2	2-7-2	2-10-2	2-14-2
Tensile un folded (MD)	N/cm	100	160	170	190	220	270	330	400
Tensile un folded (XD)	N/cm	80	90	105	120	150	200	300	350
Tensile folded (MD)	N/cm	80	90	100	110	130	200	250	300
Tensile folded (XD)	N/cm	50	70	90	100	120	150	200	250
Elongation un folded (MD)	%	15	15	15	15	20	20	20	20
Elongation un folded (XD)	%	20	20	20	20	20	25	25	25
BDV un folded	kV	6	8	11	12	14	19	23	28
BDV folded	kV	5	7	9	10	12	15	18	20

Reference standard – IEC 6026-3: 2008 sheet no 312 Nomex<sup>®</sup> is a registered trademark of **DuPont**<sup>™</sup>

#### Hatim Dielectrics Private Limited

17/11 & 17/12 K B Sarani (Mall Road), Dum Dum, Kolkata 700 080 (India)

+91 33 4044 5152 / 4044 5252 / 4064 5151

www.hatimdielectrics.in

info@hatimdielectrics.in



The information and data contained herein are believed to be accurate and reliable, however since Hatim Dielectrics cannot be aware of all the applications to which its products may be put, or control subsequent processing, Hatim Dielectrics can make no warranties conforming the fitness or suitability for a particular use or purpose. Any proposed application of Hatim Dielectrics' products should be thoroughly tested and satisfactory performance independently confirmed by the user.